



7860 E- 3M TT2 GW PET 50-300E-65WG

Thermal Transfer Polyester Label Material

Product Data Sheet

Issued February 2002
Supersedes July 2001

Physical Properties

Not for specification purposes
(Calipers are nominal values)

| | |
|-------------------|--|
| Facestock | 53 micron Gloss Radiant White polyester |
| Adhesive | 20 micron #300 E Acrylic |
| Liner | 56 micron, 62 g/m ² White Densified Glassine |
| Shelf Life | 24 months from date of manufacture of product when properly stored between 22°C and 50% relative humidity. |

Features:

- Facestock is topcoated for thermal transfer printing. Resin ribbons are recommended for optimum durability. The topcoat also provides improved ink anchorage for traditional forms of press printing.
- #300 adhesive bonds well to a wide variety of substrates including metals, high surface energy (HSE) plastics and low surface energy (LSE) plastics. It is ideal for applications requiring high initial adhesion especially to LSE plastic surfaces.
- 62 g/m² densified glassine liner assures consistent die cutting.
- 3M™ Label Material 7860 E UL recognised (File MH 18072). See UL listings for details, cUL approvals pending.

Application Ideas:

- Barcode labels and rating plates.
 - Property identification and asset labelling in harsh environments.
 - Warning, instruction, and service labels for durable goods.
 - Nameplates for durable, electronic and sporting goods.
-

Performance Characteristics
 Not for specification purposes

| Adhesion | 90° Peel Adhesion, Test procedure FTM 2 | | | |
|-----------------|---|-------|---|-------|
| | Initial (20 Minute Dwell/RT) | | Ultimate Adhesion 72 Hours Dwell at 70° C | |
| | N/10mm | Oz/In | N/10mm | Oz/In |
| Aluminium | 4.2 | 38 | 5.6 | 50 |
| Stainless Steel | 4.5 | 41 | 5.6 | 50 |
| Phenolic | 4.3 | 39 | 5.4 | 48 |
| ABS | 4.6 | 41 | 5.5 | 50 |
| Polycarbonate | 5.0 | 45 | 5.3 | 48 |
| Polystyrene | 4.7 | 42 | 5.1 | 46 |
| Polypropylene | 4.4 | 40 | 4.7 | 42 |
| HD Polyethylene | 3.0 | 27 | 3.6 | 32 |
| LD Polyethylene | 3.5 | 32 | 3.4 | 31 |
| Powder Coating | 3.0 | 27 | 5.2 | 47 |

| Surface | Conditioned for 3 Days at -40°C | |
|-----------------|---------------------------------|-------|
| | 90° Peel | |
| | N/10mm | Oz/In |
| Aluminium | 4.3 | 39 |
| Stainless Steel | 4.9 | 44 |
| Phenolic | 4.7 | 42 |
| ABS | 5.2 | 47 |
| Polycarbonate | 5.0 | 45 |
| Polystyrene | 5.0 | 45 |
| Polypropylene | 4.8 | 43 |
| HD Polyethylene | 3.5 | 32 |
| LD Polyethylene | 5.0 | 45 |
| Powder Coating | 4.0 | 36 |

Performance Characteristics Contd.

| | | |
|------------------------|---|--|
| Temperature Resistance | 149°C for 24 hours: | no significant visual change 0.7% MD shrinkage 0.9% CD shrinkage |
| | -40°C for 3 days: | no significant visual change |
| Humidity Resistance | 24 hours at 38°C and 100% relative humidity | no significant changes in appearance or adhesion |

| | | | | |
|----------------------------------|--|--------------|-------------------|-------------------------|
| Environmental Performance | The properties defined are based on four hour immersions at room temperature 22°C unless otherwise noted. Samples were applied to stainless steel panels 24 hours prior to immersion and were evaluated one hour after removal from the solution for peel adhesion. Adhesion measured at 90° peel angle (FTM 2) at 305 mm/min. | | | |
| Chemical Resistance | Adhesion to Stainless Steel | | Appearance | Edge Penetration |
| Chemical | N/10mm | Oz/In | Visual | Millimetres |
| Heptane | 3.8 | 34 | No change | 5 |
| Petrol | 3.2 | 29 | No change | 4 |
| Diesel | 4.8 | 43 | No change | 1 |
| SAE 15W40 Engine Oil | 5.5 | 50 | No change | 0 |
| Dot 4 Brake Fluid | 5.6 | 50 | No change | 0 |
| Screen Wash | 7.0 | 63 | No change | 0 |
| IPA | 5.3 | 48 | No change | 1 |
| Toluene | 3.1 | 28 | No change | 5 |
| MEK | 3.2 | 29 | No change | 5 |
| Lemsolve | 5.0 | 45 | No change | 2 |
| Teepol Detergent | 3.6 | 32 | No change | 0 |
| PH 4 | 7.0 | 63 | No change | 0 |
| PH 10 | 6.6 | 59 | No change | 0 |
| 409 Solution | 6.4 | 58 | No change | 0 |

Agency Listing Information

Thermal Transfer Printing:

UL approved with the following thermal transfer ribbons

Armor: AXR-8+
Ricoh™: B110CX
Sony™: TR 5070
Astromed R5, RY
Kurz 501
limak SP- 330

Press Inks:

For details of inks compatible with this labelstock that meet the requirements of both UL, please contact your local technical service engineer.

Processing

Printing:

Facestock is topcoated for improved ink receptivity and is designed for thermal transfer printing. It is printable by all standard roll-processing methods including flexography, hot stamp, letterpress, and screen-printing.

Die Cutting:

Rotary die cutting is recommended. Fanfolding of labels is not recommended. Small labels should be evaluated carefully. Winding tensions should be kept at a minimum to help prevent the adhesive from oozing.

Packaging:

Finished labels should be stored in plastic bags.

Special Considerations

For maximum bond strength, the surface should be clean and dry. Typical cleaning solvents are heptane and isopropyl alcohol.

NOTE: When using solvents, read and follow the manufacturer's precautions and directions for use.

For best bonding conditions, application surface should be at room temperature or higher. Low temperature surfaces, below 5°C can cause the adhesive to become so firm that it will not develop maximum contact with the substrate. Higher initial bonds can be achieved through increased rubdown pressure.

3M is a trademark of the 3M Company.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.

* Trademarks listed are the property of their respective owners



Tapes & Adhesives Group

© 3M United Kingdom PLC 2002

3M United Kingdom PLC
3M House, PO Box 1,
Market Place,
Bracknell, Berkshire,
RG12 1JU

Product Information :
Tel 0870 60 800 50
Fax 0870 60 700 99

3M Ireland
3M House, Adelphi Centre,
Upper Georges Street,
Dun Laoghaire, Co. Dublin,
Ireland

Customer Service :
Tel (01) 280 3555
Fax (01) 280 3509