



Strapping Tape 6876

Product Data Sheet

January 2012

Product Description

3M strapping tape 6876 is a clean-removal tape made of tensilized blue polypropylene backing film coated with a pressure sensitive rubber adhesive.

The tape is designed to secure appliance parts and electronic components in place during manufacture and shipment.

Typical Physical Properties and Performance Characteristics

Not for specification purposes

		Test Method
Backing type	Tensilized PP	-
Adhesive	Natural Rubber	-
Backing Thickness	0.057mm	AFERA-5006
Total Thickness	0.070 mm	AFERA-5006
Adhesion to Steel	2.0 N/10mm	AFERA-5001
Tensile Strength	150 N/cm	AFERA-5004
Elongation	35%	AFERA-5004
Color	Blue	-

Storage	Store in original carton under normal conditions of 15-25°C and 40-50% relative humidity
Shelf Life	12 months from date of despatch by 3M
For Additional Information	To request additional product information or to arrange for sales or technical assistance call 3M Poland, see address below.
Important Notice	All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method or application. All questions of liability relating to this product are governed by the terms of the sale subject, where applicable, to the prevailing law

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations

3M is a trademark of the 3M Company.

